

**ADDENDUM TO PINK SHEETS**  
**Designations and Chemical Composition Limits for Aluminum Alloys**  
**in the Form of Castings and Ingot**

**February 17, 2022**

Alloy Designation and Chemical Composition Limits Registered Since Publication of 2018 Edition of the Pink Sheets																						
Designation			Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ag	Be	Pb	Sn	Zr		FNs	OTHERS <sup>12</sup>		Al	
AA No.	Date REGISTERED	PRODUCTS <sup>5</sup>																	Each	Total <sup>3</sup>	Minimum	
527.0	2021-03-05	Casting	-	-	-	-	9.5-10.0	-	-	-	-	-	-	-	-	-	-	Ce 7.2-8.8	-	0.10	0.50	Rem.
527.1	2021-03-05	Ingot	-	-	-	-	9.7-10.0	-	-	-	-	-	-	-	-	-	-	Ce 7.4-8.8	-	0.08	0.40	Rem.
727.0	2021-03-05	Casting	-	0.25-0.50	-	-	2.3-2.7	-	0.6-0.7	5.7-6.0	-	-	-	-	-	-	-	Ce 3.5-4.0	-	0.10	0.50	Rem.
727.1	2021-03-05	Ingot	-	0.25-0.45	-	-	2.4-2.7	-	0.6-0.7	5.7-6.0	-	-	-	-	-	-	-	Ce 3.6-4.0	-	0.08	0.40	Rem.

Unless specified below, for referenced footnotes refer to the Pink Sheets as applicable.