

**ADDENDUM TO 2006 CLAD SHEETS**  
**Components of Clad Aluminum Alloy Products**

**July, 2015**

New Registrations							
Designation	Component Alloys (1)		Total Thickness of Composite Product In.	Sides Clad	Cladding Thickness per Side (Percent of Composite Thickness)		
	Core	Cladding			Nominal	Average (2)	
						min	max
Alclad 2029 Sheet and Plate	2029	1230	0.032-0.062 0.063 and over	Both Both	5 2.5	4 2	- -

Unless specified below, for all referenced footnotes refer to the Clad Sheets as applicable.